

processing sheet

futado „Fixgrund“ / Status: 09.2021

Substrates

The substrate must be dry, solid, clean and free of grease. Remove loose wallpaper, glue paints and poorly adhering coatings.

Pre-treat extremely absorbent or porous substrates with depth primer. If in doubt, create a test area.

For substrate preparation and application, observe VOB, Part C, DIN 18363 and the relevant BFS data sheets.

Caution: Old tile coverings must be subjected to basic cleaning!
Not suitable for floating substrates (wooden beams,-ceiling, etc.)

Notes

For proper processing, the materials should be stored for 24-48 h before processing at a room temperature of at least 15°C.

Processing

Futado Fixgrund should be applied undiluted with a short pile roller or brush.

Drying time after approx. 6 hours (depending on the absorbency of the substrate, temperature and air humidity - longer in unfavorable ambient conditions).

Note: By adding 5 % water, a better distribution on the surface is possible.

Working temperature

The materials should be stored for 24-48 h before processing at a room temperature of min. 15°C for proper processing.

For expert working keep the material ideally 24-48h before processing at a roomtemperature of min. 15°C.

Do not apply below +8 °C air and object temperature. Ideal for

application at air and object temperatures between +15 °C and +25 °C.

Drying time

Approx. 6 hours at > +20°C and 50% relative humidity, lower temperatures as well as insufficient ventilation situations require longer drying times.

At lower temperatures, as well as insufficient ventilation, longer drying times are to be expected.

Safety instructions

Avoid contact with the eyes and skin. We recommend wearing work gloves and protective goggles. Keep safe from children.

Notes

The content does not establish a contractual legal relationship and is only non-binding advisory. The processor/buyer is not released from the responsibility of testing our products for their suitability for the intended application.

In addition, our General Terms and Conditions of Business apply. With the publication of a new edition of this data sheet with a new status, the previous information loses its validity.

The current version can be found at volimea.de.



Suitable for allergy sufferers



Natural ingredients



High quality and tested products



Strong adhesive force



High quality and tested products

VOLIMEA GmbH & Cie. KG products are manufactured exclusively for professional applicators who have a basic knowledge of the handling and use of chemical and technical products for surface design. The processing instructions for our qualities given in the data sheets are to be regarded exclusively as non-binding recommendations and do not constitute any guarantee. These recommendations are based on our experience and test series and are intended to facilitate the work of our customers. Any possible deviation from the ideal working conditions is the responsibility of our customers and may affect the result of the application. However, this does not release the customer from his obligation to check the product and its suitability for the surface to be treated, preferably by trial application. In case of any doubts regarding the handling or processing of the purchased product, our sales staff and technicians will provide you with information to the best of their knowledge. It goes without saying that VOLIMEA GmbH & Cie. KG guarantees the perfect quality of its products in accordance with the respective product specifications, but the responsibility for the use of the products supplied lies exclusively with the purchaser. Unless we have expressly warranted specific properties and suitability of the products for a contractually determined purpose, any advice or information on application technology, although given to the best of our knowledge, is in any case non-binding and does not constitute a warranty of any kind. VOLIMEA shall be liable for the use of its products by its customers in accordance with its General Terms and Conditions of Sale and Delivery, to which the customer's attention is hereby drawn. The current Technical Data Sheet can be downloaded from our website. After publication of a new edition, the validity of previous technical data sheets expires. Status: 2020-01-13.